

ANNEXURE 1

SPECIFICATION OF NYLON STRING

Nylon woven braided string made from high tenacity multifilament nylon yarn, 3.0 mm diameter, having an inner core made from 3 (three) strands. The string shall have a minimum breaking strength of 90 Kgs and an elongation of about 15-18%.

The string should be supplied in a length of 500 or 1000 m without joints in between woven in a wooden drum/spool. Each drum/spool shall have clear sticker containing the length of the string.

Offer must accompanied with 25 meters of sample for testing; failing which offer will be rejected with no further consideration / communication. Offer must contain weight of the offered material per meter length.

A handwritten signature in black ink, consisting of a large, stylized 'G' followed by a horizontal line and a small flourish.